

CLAIMS

What is claimed is:

- 5 1. A method of surface pretreatment before selective epitaxial growth process, comprising:
 providing a semiconductor substrate having metal-oxide-semiconductor devices formed thereon;
 performing a dry etching process with a carbon-free plasma source to
10 remove a portion of said semiconductor substrate; and
 performing a selective epitaxial growth process to form a semiconductor layer on said semiconductor substrate.
2. The method of claim 1, wherein said dry etching process is performed
15 with a carbon-free plasma source containing hexafluorosulfur (SF_6) diluted with ambient gas.
3. The method of claim 2, wherein said dry etching process is performed
20 with a carbon-free plasma source containing hexafluorosulfur (SF_6) diluted with ambient gas selected from a group consisting of helium, neon, argon, hydrogen and nitrogen.
4. The method of claim 2, wherein said dry etching process is performed
25 with a carbon-free plasma source containing hexafluorosulfur (SF_6) having a volume ratio between about 0.5% and 5% .

5. The method of claim 3, wherein said dry etching process is performed with a carbon-free plasma source containing hexafluorosulfur (SF_6) having a volume ratio between about 0.5% and 5% .

5 6. The method of claim 4, wherein said dry etching process is performed at a pressure about 10 mtorr and a power between about 20 watts to about 500 watts, and an etching time within about 1 minutes.

7. The method of claim 5, wherein said dry etching process is performed
10 at a pressure about 10 mtorr and a power between about 20 watts to about 500 watts, and an etching time within about 1 minutes.

8. The method of claim 1, wherein said dry etching process is performed to remove said semiconductor substrate about 20-50 angstroms.

15 9. The method of claim 2, wherein said dry etching process is performed to remove said semiconductor substrate about 20-50 angstroms.

10. The method of claim 1, wherein further comprising a baking process
20 performed with hydrogen ambient gas at a temperature less than 750°C prior to said selective epitaxial growth process.

11. A method of forming a semiconductor device using selective epitaxial growth, comprising:

25 providing a semiconductor substrate with a first conductivity;

forming a plurality of isolation regions on said semiconductor substrate;
sequentially forming a gate dielectric layer and a gate electrode on said semiconductor substrate between each pair of said isolation regions;

forming a lightly doped drain region with a second conductivity opposite
5 to said first conductivity in said semiconductor substrate between said gate electrode and each said isolation region;

forming a first spacer around said gate dielectric layer and said gate electrode;

forming a source/drain region with said second conductivity beside said
10 lightly doped drain region;

performing a dry etching process with a carbon-free plasma source to remove a portion of said semiconductor substrate;

performing a selective epitaxial growth process to form a semiconductor layer on said semiconductor substrate;

15 forming a metal layer on said semiconductor layer; and

performing a salicide process to form a silicide layer on said semiconductor substrate.

12. The method of claim 11, wherein said dry etching process is
20 performed with a carbon-free plasma source containing hexafluorosulfur (SF_6) diluted with ambient gas.

13. The method of claim 12, wherein said dry etching process is performed with a carbon-free plasma source containing hexafluorosulfur (SF_6)
25 diluted with ambient gas selected from a group consisting of helium, neon, argon, hydrogen and nitrogen.

14. The method of claim 12, wherein said dry etching process is performed with a carbon-free plasma source containing hexafluorosulfur (SF₆) having a volume ratio between about 0.5% and 5% .

5

15. The method of claim 13, wherein said dry etching process is performed with a carbon-free plasma source containing hexafluorosulfur (SF₆) having a volume ratio between about 0.5% and 5% .

10 16. The method of claim 14, wherein said dry etching process is performed at a pressure about 10 mtorr and a power between about 20 watts to about 500 watts, and an etching time within about 1 minutes.

15 17. The method of claim 15, wherein said dry etching process is performed at a pressure about 10 mtorr and a power between about 20 watts to about 500 watts, and an etching time within about 1 minutes.

20 18. The method of claim 11, wherein further comprising a baking process performed with hydrogen ambient gas at a temperature less than 750°C prior to said selective epitaxial growth process.

19. The method of claim 11, wherein further comprising a step of forming a second spacer around said gate dielectric layer and said gate electrode prior to forming said first spacer.

25

20. The method of claim 11, wherein said metal layer is selected from a group consisting of Ti, Co, Ta, Ni, Pt and a compound thereof.